

# PITTWRAP® SS PRIMER PRODUCT DATA SHEET

**FOAMGLAS**  
Industry

IMPORTANT: MATERIAL SAFETY DATA SHEETS ARE AVAILABLE AND SHOULD BE READ BEFORE USING THIS PRODUCT.

## DESCRIPTION:

PITTWRAP® SS Primer is specially formulated to promote adhesion of PITTWRAP® self-sealing jacketing when the laps are slightly dusty or the application is below 10°C (50°F).

## \*TYPICAL PROPERTIES:

PROPERTY	
Color:	Translucent White
Appearance:	Thin Liquid
Solids, %wt:	21
Weight: kg/l (lbs/gal):	0.92 (7.7)
Coverage: m <sup>2</sup> /l (ft <sup>2</sup> /gal)	7.4 (75)
Application Temp: °C, (°F):	-7 to 38 (20 to 100)
Flammability:	
Wet	Flammable
Dry	Combustible
Flash Point, closed cup, °C (°F):	4 (40)
Service Temperature °C, (°F)	-56 to 82, (-70 to 180)
Solvent:	Toluene

\* Properties subject to change. Consult Pittsburgh Corning Corporation.

## MATERIAL PREPARATION:

Stir well before using. Keep container closed when not in use. See Caution Statement.

## APPLICATION INSTRUCTIONS:

Apply a thin coat of primer to the bituminous side of the jacketing lap with a brush or swab. Allow the solvent to evaporate for a few minutes before seal is made. Press lap and roll completed joint with a hard roller such as a wallpaper seam roller. Check for unsealed areas along the seam and repress or reseal before back filling. See one of the PITTWRAP® self-sealing jacketing product data sheets (FI-179A), (FI-234), or (FI-235) for details of jacketing application.

## LIMITATIONS:

PITTWRAP® SS Primer is not a gap-filling sealant. It is used only to assist in making a bond. Keep lap area free of dust and dirt.

Use primer on jacketing only when necessary because of dust or application temperature below 10°C (50°F). Use only on the bituminous side of the jacketing. Solvent may attack organic foams.

PACKAGING: 3.8 liter (1 gal.) container

The information contained herein is accurate and reliable to the best of our knowledge. But, because Pittsburgh Corning Corporation has no control over installation workmanship, accessory materials or conditions of application, NO EXPRESS OR IMPLIED WARRANTY OF ANY KIND, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, IS MADE as to the performance of an *installation* containing Pittsburgh Corning Products. In no event shall Pittsburgh Corning be liable for any damages arising because of product failure, whether incidental, special, consequential or punitive, regardless of the theory of liability upon which any such damages are claimed. Pittsburgh Corning Corporation provides written warranties for many of its products, and such warranties take precedence over the statements contained here

FOAMGLAS® and PITTWRAP® are federally registered trademarks owned by Pittsburgh Corning Corporation

Pittsburgh Corning Corporation  
800 Presque Isle Drive Pittsburgh, PA 15239-2799  
USA  
Toll Free: 800-545-5001  
Phone: (724)327-6100 Fax: (724)387-3806  
<http://www.foamglas.com/>

Pittsburgh Corning Europe S.A./ N.V.  
(EMEA Headquarters)  
Albertkade 1  
3980 Tessenderlo  
Belgium  
Phone: +32-13-611-415  
Fax: +32-13-351-567