

PC[®] FABRIC 79

Product Datasheet

1. Description and Area of Application

PC[®] Fabric 79 is an open mesh, synthetic fabric for reinforcing coatings applied over FOAMGLAS[®] insulation. The large mesh openings allow the coating to easily penetrate and bond to the insulation and fabric. The thickness of the fabric assures that the proper thickness of the coating is applied and gives the required strength. The high elongation accommodates large and mechanical movements without rupture and allows maximum movement of the coating.

2. Field Application

Always read and understand information contained within product datasheets and safety datasheets before attempting to use this product. If you have questions regarding fitness of use of this product for an application, consult Pittsburgh Corning LLC.

Substrate Preparation

The FOAMGLAS[®] insulation surface should be dry, free of frost, oil and grease.

Cellular Glass Application Guidelines

PC[®] Fabric 79 is cut to fit piping, vessel or shape, allowing a minimum of 5 to 8 cm (2 to 3 in.) overlap at all seams.

Fabric should be cut to fit closely without wrinkles. Scissors or shears are recommended for cutting.

Follow instructions on the Product Datasheet for the specific coating to be used.

PC[®] Fabric 79 should not be exposed after second application of wet coating, but the profile of fabric pattern may be visible in dried coating.

Clean up and Disposal

Dispose of excess fabric in accordance with local, state and federal regulations.

3. Type of Delivery and Storage

- Rolls: 1 x 45.7 m (39.4 in. x 50 yards)
- Weight per roll 3.9 ± 0.6 kg (8.7 ± 1.3 lb)
- Store in a dry location.
- Consult Safety Datasheet for additional storage and handling information.



4. Coverage

Standard application of coating to FOAMGLAS® insulation:

- Roll: Will cover approximately 42 m² (452 ft²)
- Required number of rolls, N, of PC® Fabric 79:

Equation 1: SI, Metric Units, $N = 1.08 \cdot A \div 45.7$

Equation 2: Imperial units, $N = 1.08 \cdot A \div 492$

Where A is the actual surface area to be covered in m² or ft².

- All figures exclude losses.

5. Typical Properties

PROPERTY ^A	METHOD	SI	ENGLISH
COLOR			White
COMPOSITION			100% Polyester
MESH DENSITY		2.4 x 2.0 / cm	6 x 5.5 / in.
MESH OPENING (WIDTH)		3.18 mm	0.125 in.
THICKNESS, NOMINAL		0.67 ± 0.13 mm	0.026 ± 0.005 in.
STRENGTH, MINIMUM	BALL BURST	7.0 kg / cm ²	100 psi
WEIGHT, NOMINAL		94.3 ± 14.2 g / m ²	2.78 ± 0.42 oz / yd ²
REACTION TO FIRE			Combustible

^A Properties subject to change. Consult Pittsburgh Corning LLC.

6. Limitations

- Refer to product data sheet of approved coatings for service limitations.

The information contained herein is accurate and reliable to the best of our knowledge. But, because Pittsburgh Corning LLC has no control over installation workmanship, accessory materials or conditions of application, NO EXPRESSED OR IMPLIED WARRANTY OF ANY KIND, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, IS MADE as to the performance of an installation containing Pittsburgh Corning LLC products. In no event shall Pittsburgh Corning LLC be liable for any damages arising because of product failure, whether incidental, special, consequential or punitive, regardless of the theory of liability upon which any such damages are claimed. Pittsburgh Corning LLC provides written warranties for many of its products, and such warranties take precedence over the statements contained herein.

Pittsburgh Corning LLC
One Owens Corning Parkway
Toledo, OH 43659 USA

To contact by phone or email:

Industrial & Commercial Sales

Technical Services

For web-based Sales and Technical
Service inquiries, please visit
www.foamglas.com.

Americas

+1 724 327 6100

+1 800 327 6126

Asia-Pacific

Singapore: + 65 9635 9184

China: +86 (0) 21 6140 8002

Japan: + 81 50 7554 0248

Europe, Middle East & Africa

+32 13 661 721

Americas & Asia Pacific

+1 800 327 6126

foamglastechnical@owenscorning.com

Europe, Middle East & Africa

+32 13 611 468

Industrytechnical@foamglas.com