

PITTWRAP® CF TAPE

Product Datasheet

1. Description and Area of Application

PITTWRAP® CF Buttstrip is a tri-directionally reinforced, multi-layer laminate facing tape coated with a cold-weather acrylic pressure-sensitive adhesive. PITTWRAP® CF Buttstrip designed as a self-adhesive butt strip system for sealing butt joints of PITTWRAP® CF jacketed FOAMGLAS® pipe insulation.

2. Field Application

Scissors or a sharp utility knife can be used to cut PITTWRAP® CF Tape. Work can be carried out during weather conditions normal to construction.

Substrate Preparation

All surfaces should be dry and free of dust, loose scale, oil, grease and frost.

Cellular Glass Application Guidelines

Apply the PITTWRAP® CF Tape directly over the edge of the PITTWRAP® CF jacketing that will be covered by the overlap, removing the release paper as you go.

Apply even pressure to butt strip to avoid puckering. Use a rubber roller to ensure sufficient bonding.

Clean up and Disposal

Dispose of excess tape, release film and packaging in accordance with local, state and federal regulations.

3. Type of Delivery and Storage

- Rolls: 38 mm x 183 m (1.5 in. x 600 ft), 8 Rolls per box, Weight approx. 1.3 kg (2.8 lb) per roll.
- Stored on end, under cover and protected from mechanical damage.
- Store away from ignition sources.
- Consult Safety Datasheet for additional storage and handling information.

4. Coverage

Standard application of jacketing to FOAMGLAS® insulation:

Approximately one roll of PITTWRAP® CF Tape will seal approximately 182.9 m (600 ft.) of jacket lap.



5. Typical Properties

PROPERTY ^A	METHOD	SI	ENGLISH
COLOR			Yellow
THICKNESS, TOTAL LAMINATE – RELEASE FILM	PSTC-133	0.09 mm	3.6 mil
APPLICATION TEMPERATURE, MINIMUM		10 °C	50 °F
SERVICE TEMPERATURE ^B			
MAXIMUM		104 °C	220 °F
MINIMUM		-40 °C	-40 °F
PEEL ADHESION	PSTC-101	11.1 N / 25 mm	40 oz / in.
SHEAR ADHESION (AFTER 24 HRS)	PSTC-107	15.2 kPa	2.2 psi
TENSILE STRENGTH	PSTC-131	90.4 N / 25 mm	20 lb / in.
ELONGATION	PSTC-101		110%
PERMEANCE	ASTM E96 (Wet Cup)	16.6 ng / Pa·s·m ²	0.29 perm

^A Properties are subject to change. Consult Owens Corning.

^B Service temperature limits are derived from laboratory evaluation of the product. Variations in substrates, loading conditions, or other external factors may further limit service temperature. Always consult Owens Corning FOAMGLAS® Insulation System Specification for suitability for use recommendations for a specific application.

6. Limitations

- DO NOT use below ground.
- DO NOT use outdoors without protective cladding or in areas where it can be exposed to UV radiation.
- DO NOT use where jacketing will be exposed to hydrocarbons.

The information contained herein is accurate and reliable to the best of our knowledge. But, because Pittsburgh Corning LLC has no control over installation workmanship, accessory materials or conditions of application, NO EXPRESSED OR IMPLIED WARRANTY OF ANY KIND, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, IS MADE as to the performance of an installation containing Pittsburgh Corning LLC products. In no event shall Pittsburgh Corning LLC be liable for any damages arising because of product failure, whether incidental, special, consequential or punitive, regardless of the theory of liability upon which any such damages are claimed. Pittsburgh Corning LLC provides written warranties for many of its products, and such warranties take precedence over the statements contained herein.

Pittsburgh Corning LLC
One Owens Corning Parkway
Toledo, OH 43659 USA

To contact by phone or email:

Industrial & Commercial Sales

Technical Services

For web-based Sales and Technical
Service inquiries, please visit
www.foamglas.com.

Americas

+1 724 327 6100

+1 800 327 6126

Asia-Pacific

Singapore: + 65 9635 9184

China: +86 (0) 21 6140 8002

Japan: + 81 50 7554 0248

Europe, Middle East & Africa

+32 13 661 721

Americas & Asia Pacific

+1 800 327 6126

foamlastechnical@owenscorning.com

Europe, Middle East & Africa

+32 13 611 468

Industrytechnical@foamglas.com