



FOAMGLAS® T4+

Page: 1 Date: 12.03.2018 Supersedes: 03.07.2017 www.foamglas.com



FOAMGLAS® T4+

Form of delivery (content per package)







length x width [mm]	600 x 450								
thickness [mm]	40	50	60	70	80	90	100	110	120
R _D [m²K/W]	0.95	1.20	1.45	1.70	1.95	2.20	2.40	2.65	2.90
units	12	10	8	7	6	6	5	5	4
square metre [m²]	3.24	2.70	2.16	1.89	1.62	1.62	1.35	1.35	1.08

length x width [mm]	600 x 450								
thickness [mm]	130	140	150	160	170	180	190	200	
R _D [m²K/W]	3.15	3.40	3.65	3.90	4.15	4.35	4.60	4.85	
units	4	4	3	3	3	3	3	3	
square metre [m²]	1.08	1.08	0.81	0.81	0.81	0.81	0.81	0.81	

Other dimensions and thicknesses are available on request.

General FOAMGLAS® Cellular Glass Insulation characteristics

- Description : FOAMGLAS® Insulation is manufactured from specially graded recycled glass (≥ 60%)* and natural raw materials which are available in abundant supply (sand, dolomite, lime...). The insulation is totally inorganic, contains no ozone depleting propellants, flame resistant additives or binders. Without VOC or other volatile substances.
- Reaction to fire (EN 13501-1) : Material complying with Euroclass A1, non-combustible, no toxic fumes
- Service temperature limits : from -265°C to +430°C
- Water vapour resistance (EN ISO 10456) : $\mu = \infty$
- Hygroscopicity : zero
- Capillarity : zero
- Melting point (cf DIN 4102-17) : >1000 °C
- Thermal expansion coefficient (EN 13471) : $9 \times 10^{-6} \text{ K}^{-1}$
- Specific heat (EN ISO 10456) : 1000 J/(kg·K)
- FOAMGLAS® characteristics :

				
Time-tested thermal performance	Waterproof	Resistant to attack	High compressive strength	Acid resistant / chemical resistant
				
Non-combustible	Impervious to water vapour	Dimensionally stable	Ecological	Radon protection



FOAMGLAS® T4+

Page: 2

Date: 12.03.2018

Supersedes: 03.07.2017

www.foamglas.com

1. Product characteristics according to EN 13167 ¹⁾

Density ($\pm 10\%$) (EN 1602)	: 115 kg/m ³
Thickness (EN 823) ± 2 mm	: from 40 to 200 mm
Length (EN 822) ± 2 mm	: 600 mm (half slabs 300 mm available)
Width (EN 822) ± 2 mm	: 450 mm
Thermal conductivity (EN ISO 10456)	: $\lambda_D \leq 0.041$ W/(m·K)
Reaction to fire (EN 13501-1)	: Euroclass A1
Point load (EN 12430)	: PL ≤ 1.5 mm
Compressive strength (EN 826 annexe A)	: CS ≥ 600 kPa
Bending strength (EN 12089)	: BS ≥ 450 kPa
Tensile strength (EN 1607)	: TR ≥ 150 kPa

¹⁾ CE-marking ensures conformity with the mandatory essential requirements of CPD as mentioned in EN 13167; within the CEN Keymark certification all mentioned characteristics are certified by an empowered, notified and accredited 3rd party.

2. Additional product characteristics

Thermal diffusivity at 0°C	: 4.2×10^{-7} m ² /sec
BRE Green Guide Rating	: A
Certificate natureplus	: 0406-1101-101-1
Green Spec® Listed	: yes

3. Applications

Insulation of:

- flat roofs
- façades
- belowgrade floors and walls
- metal and special roofs
- interior insulation (walls, floors, ceilings)

* $\geq 60\%$ recycled glass consists of highly selected postconsumer glass and highly selected production scrap/co-products.