


## Schematic drawing

## System 5.1



- 1 Supporting substrate, e.g. concrete deck
- 2 Primer
- 3 FOAMGLAS® TAPERED slabs, laid in hot bitumen
- 4 Two layers of bituminous waterproofing membranes
- 5 Separating / protective layer
- 6 Service or protective layer (gravel, pavement slabs, planting, etc.)

## FOAMGLAS® product properties

Waterproof – Resistant to vermin – High compressive strength – Non-combustible  
 – Impervious to water vapour – Dimensionally stable – Acid resistant – Easily cut to shape – Ecological

## Advantages of the FOAMGLAS® system


- **Quality:** Systems with high quality materials. Quality management by systematic site inspections and professional consulting.
- **Cost efficiency:** The high durability preserves maximum value and guarantees minimal maintenance costs.
- **Sustainability:** Optimum insulation and protection against moisture for generations.
- **Safety:** Compact, fully bonded insulation system preventing large-scale damages and renovations in the event of a leak caused by a puncture of the roofing membrane.
- **Functionality:** Insulation and vapour barrier in one single functional layer. Flexible and easy installation of a gradient through prefabricated tapered slabs.

## Recommendations for architects

- Normally used:  
 FOAMGLAS® TAPERED slabs T3+, T4+, S3 or F, size 450 x 600 mm.
- There may be a requirement to provide continuous plates around outlets and gutters.
- Insulation thickness to meet building regulations or project-specific U-value requirements. Please also consult our product overview. It contains information on all our products, their field of application and their specific properties.
- For the use of FOAMGLAS® under load bearing conditions, the project / structural engineer must check the admissible loads.
- **For technically correct implementation, relevant standards and guidelines must be observed.**

**Solutions for technical details and specification clauses on request.** Further proposals and solutions are available any time from our technical consultants. Updated: **01/2017**. We explicitly reserve the right to change the technical specifications. The current values can be found on our website under:



[www.foamglas.com/distributors](http://www.foamglas.com/distributors) > English > Applications





**Installation drawing**

- After the order is received, a detailed site drawing is established, taking any modifications into consideration. This drawing defines accurately the position of each individual slab.



### Roof 1


## System 5.1

### Installation instructions

- Apply bituminous primer with roller (or spraying equipment) on the clean and dry concrete surface, coverage ~ 0.3 l / m<sup>2</sup>. (1)
  - Apply the FOAMGLAS® slabs fully bonded to the substrate with hot bitumen poured from a bitumen can, with staggered and bitumen-filled butted joints. Coverage ~ 5.0 - 7.0 kg / m<sup>2</sup>, dependent on the thickness of the insulation:
- Dip a short as well as a long side of the slab in the poured bitumen and press into position against already laid slabs. Surplus bitumen spilt at the side must be removed with the next slab in order to avoid irregularities. (2 / 3)
- Possible waterproofing variation: Apply two layers of bituminous waterproofing membranes covering the entire surface. The first layer is applied using the pour and roll technique, the second (root-resistant) is torched on. Joints overlapping at least 100 mm, with staggered courses. (Combination of bituminous and synthetic waterproofing layers on request). (4)
  - Apply the separating / protective layer, with overlapping joints. (5)
  - Installation of the service or protective layer (gravel, pavement slabs, planting etc.).

### Recommendations for the contractor

- The build up and tolerances of the substrate have to be in accordance with relevant standards and guidelines.
- Substrate and ambient temperature should not be below + 5° C.
- A layer of waterproofing membrane must be applied immediately after the insulation has been installed. At the end of each day or every work interruption, all remaining naked surfaces as well as the front sides must be covered with a topcoat.
- Protective layers should be applied immediately after the application of the second waterproofing layer.
- Adequate measures should be taken in order to avoid any risks of damage by other contractors during construction.
- Protect sensitive components provided by other suppliers against blobs of hot bitumen and the effect of heat.
- **Please contact our technical consultants; they can help you by providing support or on-site assistance free of charge.**



The technical guidelines for the application and the installation of FOAMGLAS® are based on historical experience and general site practice. They do not reflect individual examples. We therefore assume no liability as to the completeness and the suitability for a specific project. Furthermore, our liability and responsibility are subject to our general conditions of sale which are not extended either by this technical data sheet nor by the consulting of our technical sales representatives.

**Pittsburgh Corning  
Europe S.A. / N.V.  
FOAMGLAS® Distributors**  
Albertkade 1  
B-3980 Tessenderlo  
Belgium